Sandplast LSR

Product properties

Spray and roller filler for dry rooms.Contain light, medium filler paste with premium filling capacity.Finish by treating with a wall covering and/or suitable ceiling or wall paint in the desired colour and gloss.

- Medium spray and roller filler
- Premium filling capacity
- Light grey

Flügger Sandplast

Labelling

Product use

Filling when smoothing out plaster, concrete, lightweight concrete and previously painted surfaces, and as a finish filler on gypsum plasterboard where the joints are filled with Sandplast 696 FOG or Sandplast LB with Marco Spark-Perf or Sheetrock plaster tape.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting.Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.Sand flat hard, slippery surfaces.Apply the filler paste and smooth out.Sand the surface and prime it before any additional treatment.

Application

Apply using airless spray or filler roller and smooth out with a filler knife.Decide your choice of tools based on the size of the surface.Apply a sufficient amount and then work and smooth out the filler paste.Cold/ heat can affect the viscosity of the material. Condensation during drying/curing must not form.Cold and increased humidity extends drying time, full curing and recoating interval.Increased temperature and low atmospheric humidity reduce drying time and full curing. Risk of shrinkage where the filler paste is not completely cured before additional treatment.Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Even surface for additional treatment.



Environmental information

Clean off the paint from tools and wash them with water. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost-free, and tightly closed

Supplementary Info

The product meets the requirements of M1: Emission Classification of Building Materials: Protocol for Chemical and Sensory Testing of Building Materials.

For this product there is issued an: Environmental Product Declaration

Technical Data

Product TypePlaster & SealantColor (plaster)Light greyDensity (kgs/l)1.1Solids Weight %55Solids Vol. %50Nominal spreading rate (m²/ltr.)1Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)86Adhesion on concrete (MPa)0.63Layer thickness (nominal mm)2Grain size (max. Mm)0.2	
Density (kgs/l)1.1Solids Weight %55Solids Vol. %50Nominal spreading rate (m²/ltr.)1Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Solids Weight %55Solids Vol. %50Nominal spreading rate (m²/ltr.)1Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Solids Vol. %50Nominal spreading rate (m²/ltr.)1Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Nominal spreading rate (m²/ltr.)1Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Min. working temp. during application and drying/curingMin. +10°CHumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
HumidityMax. humidity 80 % RHDrying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Drying time at 20° C, 60 % RH (Hours)2Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Recoatable at 20° C, 60 % RH (Hours)20Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	Н.
Fully cured at 20° C, 60 % RH (Days)28Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	
Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)86Adhesion on concrete (MPa)0.63Layer thickness (nominal mm)2	
Adhesion on concrete (MPa) 0.63 Layer thickness (nominal mm) 2	
Layer thickness (nominal mm) 2	
Grain size (max. Mm) 0.2	
Cleaning of Tools etc. Water	

Current TDS Version

March 2024

Replaces TDS Version

October 2023