

Wood Tex Wood Oil

Product properties

Aqueous wood oil with water-repellent properties. Protects the surface of the wood while also ensuring that the structure and vein structure are visible. Pigmented wood oil provides the best protection against the sun's harmful UV rays. Prevents the formation of mould and mould growth on the surface.

- Visible vein structure and structure
- Water-repellent surface
- Aqueous wood oil



Labelling



The product is a declared item in the Supply Chain Declaration Portal (SCDP) for New Buildings generation 4.

Product use

Wood decking, picket fences and garden furniture.

Light and dark weather-resistant types of wood and pressure-impregnated wood.

Substrate

Must be absorbent, clean, dry, solid and suitable for surface treatment.

For substrates which has not been previously treated with varnish, paint or opaque wood stain.

Insufficiently protected cross-cut wood, water traps or the risk of water accumulation must not occur.

The moisture level in the wood prior to paint treatment max.: 18%.

Treatment

Wood stain, paint and decayed wood fibres must be completely removed by cleaning and sanding.

Remove dirt, filth, grease and chalking material with Terrace Cleaner.

Algae, mould and mildew must be removed by cleaning with Facade Anti-green.

Untreated or previously oiled surfaces are sanded with sandpaper grain 80 before oiling.

Application

Apply with a brush or roller and work thoroughly into the wood.

Choose appropriate tools for the desired finish.

Apply wet-on-wet, and finish by brushing in the same direction.

Repeat the process until the wood is saturated with an uniform appearance without the formation of a varnish layer. Wipe off excess wood oil.

Condensation must not form.

Avoid working in direct sunlight.

Cold weather and high atmospheric humidity increase the drying time, complete curing and re-treatment interval.

High temperature and low atmospheric humidity reduce the drying time and complete curing.

Always apply test treatments to check and accept the adhesion and result.

Expected result

Colourless or transparent.

Expected durability 1 year.

The durability of the surface depends on wood quality, construction, how it is applied and exposure.

The expected durability can therefore be shorter or longer than stated.

Best penetration and durability is achieved when new or untreated wooden surfaces are sanded with sandpaper grain 80 before oiling.

Colorless treatment reduces durability.

Cleaning and maintenance

Clean the surface and repair any damage once a year or as needed.

Remove dirt, filth, grease and chalking material with Terrace Cleaner.

Algae, mould and mildew must be removed by cleaning with Facade Anti-green.

Please note!

Protect freshly painted surface from adverse weather conditions.

Take appropriate measures against the effects of moisture and rainfall on freshly painted surfaces.

The surface achieves maximum robustness when fully cured.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

| | |
|---|------------------------|
| Product Type | Wood Oil |
| Density (kgs/l) | 1.01 |
| Solids Weight % | 22 |
| Solids Vol. % | 21 |
| Nominal spreading rate (m ² /ltr.) | 6 |
| Long spreading rate (m ² /l.) | 10 |
| Short Spreading rate (m ² /ltr.) | 4 |
| Min. working temp. during application and drying/curing | Min. +10°C |
| Humidity | Max. humidity 80 % RH. |
| Drying time at 20° C, 60 % RH (Hours) | 6 |
| Recoatable at 20° C, 60 % RH (Hours) | 24 |
| Fully cured at 20° C, 60 % RH (Days) | 28 |
| Dilution | Do not dilute |
| Cleaning of Tools etc. | Water and soap |

Current TDS Version

December 2024

Replaces TDS Version

November 2024