

Interior Easy Finish 40

Product properties

Thick acrylic enamel with a gelatinous, non-drip consistency which gives a high layer thickness, good hiding power and reduces tendency for the paint to run. Recommended for subjects where there are aesthetic and medium functional requirements.

- Easy and quick to apply
- Rich surface
- Semi-gloss surface



Labelling



Product use

Doors, door frames, profiled boards, casings and skirting boards as well as iron and metal with anti-corrosion protection indoors.

Substrate

Must be primed, clean, dry, solid and suitable for paint treatment.

Treatment

Remove loose material and paint by cleaning and sanding.

Remove dirt, filth, grease and chalking material with Fluren 37.

Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49 and treated with Iso Primer.

Hard, smooth substrates must be sanded matt and primed if needed with Fix Primer.

Cracks, unevenness and holes must be filled.

New or bare cleaned wood must be primed with Stop Primer.

Apply 1-2 coats. Some colours require additional treatments.

Application

Brush, roller or spray

Choose appropriate tools for the desired finish

Apply wet-on-wet, and finish by brushing/rolling in the same direction

Always use the same batch number for continuous/unbroken surfaces

Differences in surface texture may result in shade deviations

Cold or heat can affect the material's viscosity

Material temperature when spraying must be min. 12 °C.

Condensation must not form during drying/curing

Cold weather and high atmospheric humidity extend the drying time, complete curing and re-coat interval

High temperature and low atmospheric humidity reduce the drying time and complete curing

Always apply test treatments to check and accept the adhesion and results

Expected result

Semi-gloss surface.

Good coalescence and rich finish.

Withstands ordinary soiling, use-related wear and cleaning with universal detergent, a soft brush, water and a cloth.

Strong, especially dark shades are more delicate than light colours by wear and touch.

Chalking due to surplus pigment may occur.

Does not block strike-through from knots, water-soluble colourants, water blotches or nicotine.

Treat the surface with caution until the paint is fully cured.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost-free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Product Type	Acrylic enamel
Gloss	40;Semi Gloss
Density (kgs/l)	1.28
Solids Weight %	53
Solids Vol. %	39
Nominal spreading rate (m ² /ltr.)	8
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	6
Fully cured at 20° C, 60 % RH (Days)	28
Emission acc. to ISO 16000-9:2011 (< µg/m ² h after 28 days)	17
Washability acc. to EN-13300/ISO-11998	Class 1
Dilution	Water – does not normally need to be diluted
Cleaning of Tools etc.	Water

Current TDS Version

December 2024

Replaces TDS Version

October 2024