

# Perform Airless

## Product properties

Full-matt ceiling and wall paint. Recommended for premises without special functional requirements that are exposed to light dirt and wear and tear.

- Ceiling and wall paint
- Low gloss
- Ecolabelled



## Labelling



## Product use

Secondary rooms, storage areas, garages, storage rooms and retail shops.

Concrete, lightweight concrete, plaster, bricks, gypsumboards, fiber plaster, cement fiber boards, cement particle boards.

## Substrate

Must be clean, dry, solid and suitable for surface treatment.

## Treatment

Remove loose material and paint by cleaning and sanding.

Remove dirt, grime, grease and chalking materials with Fluren 37.

Water blotches or surfaces stained by nicotine or soot must be cleaned with Fluren 49 and treated with Stop Primer.

Hard, smooth surfaces should be sanded matt and painted with Fix Primer as required.

Cracks, unevenness and holes must be spackled.

Absorbent and porous substrates must be primed with Flügger Sealer

Priming is done with Wall Primer Perform.

Apply 1-2 times. Some colours require an extra treatment.

## **Application**

Brush, roller or spray

Decide your choice of tool/utensil depending on the finish

Apply wet on wet and finish by brushing/rolling in the same direction

Always use the same batch number on contiguous/unbroken surfaces

Differences in surface structure can result in colour deviation

Cold/heat can affect the viscosity of the material

Material temperature for spray painting, min. 12°C

Condensation during drying/curing must not occur.

Cold and increased humidity extends drying time, full curing and recoat interval

Increased temperature and low atmospheric humidity reduce drying time and full curing

Always perform a test treatment for a check and acceptance of adhesion and result

## **Good practice**

If repairs are needed, remove minor marks and dirt by cleaning.

Spot repairs are carried out with the same material/batch number as originally used.

Spot repairs are expected to be visible to a greater or lesser extent depending on colour, gloss, application method, surface, light and viewing angle.

Larger damages are repaired with edging around corners, joints and the like.

## **Expected result**

Full-matt surface with low gloss.

Vulnerable to touching and staining.

Strong especially dark shades are more delicate than light by wear and touch.

Chalking from strong shades due to excess pigment may occur.

Does not block strike-through from knots or water-soluble colourants, water stains and nicotine.

Exercise care in loading the surface until the paint is fully cured.

Risk of crackling when applied directly to surfaces treated with filler.

## **Environmental information**

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

## **Storage**

Cool, frost free and tightly closed

## **Protection equipment**

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

## **Supplementary Info**

For this product there is issued an: [Environmental Product Declaration](#)

## Technical Data

---

Gloss	Full Matte;5
Density (kgs/l)	1.45
Solids Weight %	52
Solids Vol. %	30
Nominal spreading rate (m <sup>2</sup> /ltr.)	8
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	2
Fully cured at 20° C, 60 % RH (Days)	28
Classified in accordance with EN 13300	Wet abrasion resistance: R class 4 Contrast ratio: H10 class 2 (at 8 m <sup>2</sup> /l) Gloss: G4 dead-matt Maximum grain size: S1 fine
Dilution	Water, is usually not diluted
Cleaning of Tools etc.	Water
Country of Origin	Denmark

---

## Current TDS Version

December 2024

## Replaces TDS Version

October 2024